

TECHNICAL DATA SHEET

HOT MELT NOISY TAPE FOR CARTON SEALING

T&GCS2000 - 2099

Physical properties

	u. m.	Typical value	Acceptability gap
BOPP thickness	µm	25	±5%
Total thickness	µm	42	38 ÷ 46
Tnsile strenght	kg / cm	4	3 ÷ 6
Elongation to break	%	140	110 ÷ 220
Peal adhesion	g / cm	500	≥350
Rolling ball tack	cm	1	≤ 5
Metal shear 50°C (1kg; 25mm x 25mm)	min.		>15
Shear on cardboard 23°C (1kg; 25mm x 25mm)	ore		>120
Width	mm		±1
Lenght (≤ 132m)	m		±1,5%
Lenght (> 132m)	m		±0,5%

Test methods are available on request

Tape color	Transparent, Brown, White
Adhesive	Hot Melt

Guarantee

The product and its functionality is guarantee for a period of 6 moths from delivery date